

APPLICATION FOR  
UNITED STATES PATENT

In the name(s) of

WILLIAM L. BRENNEMAN

AND

SZUCHAIN F. CHEN

for


LASER ABLATION RESISTANT COPPER FOIL

CERTIFICATION UNDER 37 CFR § 1.10

I hereby certify that this correspondence is being deposited with the United States Postal Service on this date February 11, 2004 as "Express Mail Post Office to Addressee" Mailing Label No. EL 897 896 885 US to: Mail Stop Patent Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

Gregory S. Rosenblatt

Printed name of person mailing paper



Signature of Person Mailing Paper

Gregory S. Rosenblatt  
Wiggin & Dana LLP  
P.O. Box 1832  
New Haven, CT 06508-1832  
Telephone: 203-498-4319  
Facsimile: 203-782-2889

Docket No. 102426-300

## LASER ABLATION RESISTANT COPPER FOIL

### CROSS REFERENCE TO RELATED APPLICATIONS

This patent application is a continuation in part of United States Patent Application serial number 10/727,920, entitled "Peel Strength Enhancement of Copper Laminates," that was filed on December 4, 2003 and in turn claims the benefit of U.S. Provisional Patent Application No. 60/431,013 that was filed on December 5, 2002. Both the 10/727,920 and 60/431,013 patent applications are incorporated by reference herein in their entireties.

### BACKGROUND OF THE INVENTION

1. Field of the Invention:

This invention relates to the manufacture of printed circuit boards having a copper foil layer laminated to a dielectric substrate, and more particularly to a treatment to increase the adhesion of the copper foil layer to the dielectric substrate.

2. Description of the Related Art:

Copper and copper base alloy foils are widely used in the printed circuit board industry. The foil is produced to a thickness of under 203 microns (0.008 inch) and more generally to a thickness in the range of from 5.1 microns (0.0002 inch that is known in the art as 1/8 ounce foil) to 1.0 microns (0.00004 inch). The foil is typically produced by either mechanical working or electrodeposition. "Wrought" foil is produced by mechanically reducing the thickness of a copper or copper alloy strip by a process such as rolling. "Electrodeposited" foil is produced by electrolytically depositing copper ions on a rotating cathode drum and then peeling the deposited strip from the cathode.

The copper foil is bonded to a dielectric substrate forming a printed circuit board using a lamination process. The dielectric substrate is typically a fiberglass reinforced epoxy such as FR-4 (a fire retardant epoxy) or a polyimide such as Kapton® manufactured by DuPont. The lamination process includes bonding the copper foil layer to the dielectric substrate through the use of heat and pressure. A pressure of about 300 pounds per square inch (psi), at a temperature at about 175° C for a time of up to 30 minutes will provide suitable adhesion between the layers.

To maximize adhesion, it is often desirable to roughen the surface of the foil that contacts the dielectric substrate prior to bonding. While there are a variety of techniques available to roughen or treat the foil, one exemplary technique involves the formation of a

plurality of copper or copper oxide dendrites on the foil surface. U.S. Pat. Nos. 4,468,293 and  
35 4,515,671, both to Polan et al. disclose this treatment. This treatment is referred as the  
CopperBond® treatment. CopperBond is a trademark of Olin Corporation of Norwalk, CT.  
Another electrolytic surface roughening treatment is the deposition of copper/nickel nodules  
onto the surface of the foil that contacts the dielectric substrate, as disclosed in United States  
Patent Number 5,800,930 to Chen et al. In some instances, at least one side of the foil,  
40 particularly the roughened side bearing the dendrites, may have an electrodeposited coating of  
zinc or brass applied thereto. This coating has been found to enhance the bond strength of the  
foil with the dielectric substrate.

While the use of roughened surfaces on the copper foil is effective to promote adhesion  
with the dielectric substrate, the degree of surface roughening is often restricted by the  
45 electrical performance requirements of the copper foil for high frequency applications.  
Problematically, decreasing the surface roughness to meet these electrical performance  
requirements compromises the adhesion (peel strength) between the copper foil and the  
dielectric substrate.

Another problem facing printed circuit board manufacturers using either electrolytic or  
50 wrought copper foils is the relative reactivity of the copper. As a result, copper readily stains  
and tarnishes. The stains and tarnish are aesthetically unpleasant and may be a source of  
problems during the manufacture of the printed circuit board. For example, staining of copper  
foil prior to lamination can affect both the bond strength between the foil and the dielectric  
substrate and the etching characteristics of the resultant laminate. The tarnish resistance of a  
55 copper foil may be enhanced by applying a thin (can be on the atomic scale) coating that  
contains co-deposited ions of zinc and chromium. This treatment, referred to as the P2  
treatment, is disclosed in United States Patent Number 5,022,968 to Lin et al.

The 4,515,671; 5,800,930 and 5,022,968 patents are incorporated by reference in their  
entireties herein.

60 When copper foil is laminated to a dielectric substrate it is usually then selectively  
etched to form a plurality of circuit traces. Frequently, copper foil is laminated to both sides of  
the dielectric substrate and both sides selectively etched into circuit traces. It is often desired  
to electrically interconnect circuit traces on opposing sides of the dielectric. Electrical  
interconnection may be done by drilling a hole through the dielectric and depositing an  
65 electrically conductive material in the hole to form a conductive via. A blind via extends from  
one side of the dielectric to the interface of the dielectric and the copper foil on the second side  
of the dielectric. The most accurate blind vias are formed by laser ablation of the dielectric,

such as with a carbon dioxide, CO<sub>2</sub>, laser. However, it is difficult to stop the laser at the interface and avoid ablation of the copper transforming the desired blind via into a through hole via.

There remains a need for a treatment for copper foil that provides an enhanced combination of improved adhesion to a dielectric, tarnish resistance and laser ablation resistance.

#### BRIEF SUMMARY OF THE INVENTION

In one aspect of the invention, a peel strength enhancement coating is deposited on a surface of a copper foil, which may be laminated to a dielectric substrate. The peel strength enhancement coating consists essentially of a metal and metal oxide mixture, the metal and metal oxide mixture being formed from one or more of: vanadium, niobium, tantalum, chromium, molybdenum, tungsten, manganese, technetium, and rhenium. Preferably, the metal oxide is selected from one of chromate, tungstate, and molybdate. The surface of the copper foil may be smooth, and the peel strength enhancement coating may have a thickness of between about 20 to about 200 angstroms. Silane may be deposited on the peel strength enhancement coating prior to lamination to the dielectric substrate.

In another aspect of the invention, an article comprises a copper foil having a smooth surface laminated to a dielectric substrate. A peel strength enhancement coating is disposed between the copper foil and the dielectric substrate, and the copper foil exhibits less than or equal to 10% loss of peel strength when measured in accordance with IPC-TM-650 Method 2.4.8.5 using a 1/8 inch test specimen after being immersed in 4N HCl at 60°C for 6 hours. The peel strength enhancement coating may also exhibit less than or equal to 10% edge undercut after the immersion in 4N HCl at 60°C for 6 hours.

In another aspect of the invention, a method for increasing the peel strength of a copper foil laminated to a dielectric substrate comprises: prior to lamination, immersing the copper foil in an aqueous electrolytic solution containing oxyanions formed from one or more of: vanadium, niobium, tantalum, chromium, molybdenum, tungsten, manganese, technetium, and rhenium. Preferably, the metal is selected from one of chromium, molybdenum, and tungsten. The aqueous solution may be an electrolyte solution in an electrolytic cell, and the method further comprises: passing current through the copper foil and the electrolyte solution such that a coating having a thickness of between about 20 to about 200 angstroms is deposited on the

copper foil. The method may further comprise immersing the copper foil in silane after depositing the coating on the copper foil.

In another aspect of the invention, a copper foil for lamination to a dielectric substrate comprises a layer deposited on a surface of the copper foil. The layer is formed from  
105 chromium and zinc ions or oxides and is treated with an aqueous solution containing at least 0.5% silane. The surface of the copper foil may be smooth, and the thickness of the layer may be from about 10 angstroms to about 100 angstroms.

In another aspect of the invention, a method for increasing the peel strength of a copper foil laminated to a dielectric substrate comprises: prior to lamination, co-depositing a mixture  
110 of chromium and zinc ions or oxides on surfaces of the copper or copper base alloy foil; subsequent to the co-deposition step, immersing the copper foil for at least one second in an aqueous solution containing at least 0.5% silane in deionized water; and drying the copper foil prior to lamination. The aqueous solution may be at a temperature of between about 15°C to about 30°C. Co-depositing the mixture of chromium and zinc ions or oxides may include:  
115 providing an electrolytic cell containing an anode disposed in an electrolyte solution containing chromium and zinc ions; providing the copper foil as a cathode; and electrolytically depositing the chromium and zinc ions on the copper foil. The thickness of a layer formed from the chromium and zinc ions or oxides may be from about 10 angstroms to about 100 angstroms.

120 In one embodiment, the electrolyte solution is a basic solution containing hydroxide ions from about 0.07 g/l to about 7 g/l zinc ions, and from about 0.1 g/l to about 100 g/l of a water soluble hexavalent chromium salt wherein the concentration of either the zinc ions or the chromium (VI) ions or both is less than 1.0. In this embodiment, the co-deposition step includes: immersing the copper foil in the electrolyte solution; and passing current through the  
125 copper foil and the electrolyte solution such that a current density of from about 1 milliamp per square centimeter to about 1 amp per square centimeter is provided. The electrolyte solution may consist essentially of from about 10 to about 35 g/l NaOH, from about 0.2 to about 1.5 g/l ZnO, and from about 0.2 to about 2 g/l  $\text{Na}_2\text{Cr}_2\text{O}_7 \cdot 2\text{H}_2\text{O}$ .

The details of one or more embodiments of the invention are set forth in the  
130 accompanying drawings and the description below. Other features, objects and advantages of the invention will be apparent from the description and drawings, and from the claims.

## BRIEF DESCRIPTION OF THE DRAWINGS

135 The invention will be more fully understood from the following detailed description taken in conjunction with the accompanying drawings wherein like elements are numbered alike, and in which:

FIG. 1 illustrates an electrolytic cell system for peel strength enhancement of a copper laminate according to one embodiment of the present invention;

140 FIG. 2 illustrates an electrolytic cell system for peel strength enhancement of a copper laminate according to another embodiment of the present invention;

FIG. 3a is a cross-sectional view of a copper foil laminated to a dielectric substrate before exposure to hydrochloric acid (HCl);

FIG. 3b is a cross-sectional view of a copper foil laminated to a dielectric substrate after exposure to HCl;

145 FIG. 3c is a lengthwise view of the copper foil of FIG. 3b revealing an undercut coating; and

FIG. 4 is a graph depicting percent peel strength loss as a function of percent undercut.

FIG. 5 illustrates in cross-sectional representation laser ablation to form a blind via.

150 FIG. 6 is a photomicrograph illustrating the surface morphology of a surface treatment as known from the prior art.

FIG. 7 is a photomicrograph illustrating the surface morphology of a surface treatment of the invention.

## DETAILED DESCRIPTION

155 Two surface treatments are described herein that generate high adhesion between copper foil and a dielectric substrate, even where smooth copper foil is used. The invention is equally applicable to copper or copper-base alloy foils, where “base” means that the alloy contains at least 50%, by weight, of copper. As used herein, the term “copper foil” includes copper foil and copper-base alloy foil. Also, while the invention is particularly useful for use  
160 with a smooth copper foil, the invention could be applied to copper foils having any surface finish. The term “smooth”, as used herein means a low profile surface, e.g., less than  $1\mu\text{m}$  Rz, where Rz is the average of five peak to valley distance measurements as measured using a surface profilometer.

165 Surface Treatment 1

Figure 1 illustrates a system 10 for peel strength enhancement of a copper laminate according to a first aspect of the present invention. The system 10 includes an electrolytic cell 12 for co-depositing a mixture of chromium and zinc metals or oxides on surfaces of a copper foil 14 using what is referred to herein as a P2 treatment, and a silane solution tank 16 wherein  
170 the coated copper foil 14 is immersed in an aqueous solution 18 containing silane. After leaving the silane solution tank 16, the copper foil 14 may be rinsed using deionized (DI) water and then dried before it is laminated to a dielectric substrate.

The electrolytic cell 12 includes a tank 20 containing an electrolytic solution 22, and anodes 24 between which the strip of copper foil 14 passes. The silane solution tank 16  
175 contains the aqueous solution 18 containing silane. Guide rolls 26 and 28 may be used to control the travel of the strip of copper foil 14 through the electrolytic cell 12 and the silane solution tank 16, respectively. The guide rolls 26 and 28 are manufactured from any material that does not react with electrolyte solution 22. Preferably, at least one of the guide rolls 26 is formed from an electrically conductive material, such as stainless steel, so that a current may  
180 be impressed in the strip of copper foil 14 as detailed below. Guide rolls 26 rotate at a controlled speed so that the copper foil 14 is positioned between anodes 24 for a required time as discussed below. Guide rolls 28 rotate at a controlled speed so that the copper foil 14 is immersed in the aqueous solution 18 for a required time as discussed below.

In the electrolytic cell 12, a power source (not shown) is provided so that a direct  
185 electric current may pass from the anodes 24 to the strip of copper foil (cathode) 14 by means of the electrolytic solution 22. In this way, an anti-tarnish coating with the desired composition and thickness is deposited on the foil strip 14.

The electrolytic solution 22 is an aqueous solution that consists essentially of a hydroxide source, zinc ion source and a water soluble hexavalent chromium. The hydroxide  
190 source is preferably sodium hydroxide or potassium hydroxide, and most preferably, sodium hydroxide (NaOH). The hexavalent chromium source may be any water soluble hexavalent chromium compound such as  $\text{Na}_2\text{Cr}_2\text{O}_7 \cdot 2\text{H}_2\text{O}$ .

In its broadest compositional range, the electrolyte solution 22 consists essentially of from about 5 to about 100 grams per liter (g/l) of the hydroxide, from 0.07 up to about 7 g/l of  
195 zinc ions supplied in the form of a water soluble zinc compound such as ZnO, and from 0.01 to about 100 g/l of a water soluble hexavalent chromium salt. Provided, however, that at least one of the zinc ion or chromium (VI) ion concentrations is less than 1.0 g/l. In a preferred embodiment, the electrolyte contains from about 10 to about 40 g/l NaOH, from about 0.16 to

about 2 g/l zinc ions, most preferably be in the form of 0.2 to about 1.6 g/l Zn ions and from  
200 about 0.08 to about 30 g/l Cr(VI) ions most preferably be in the form of from about 0.2 to  
about 0.9 g/l Cr(VI) ions.

With each of the electrolyte solutions 22 described herein above, it is believed that an  
effective concentration of a surfactant such as lauryl sulfate will provide a more uniform  
surface.

205 The pH of the electrolyte solution 22 is maintained as basic. A pH in the range of from  
about 12 to 14 is preferred. The electrolyte solution 22 readily operates at all temperatures  
from room temperature up to about 100° C. For maximum deposition rates, it is preferred to  
maintain the electrolyte solution 22 temperature in the range of about 35° C to about 65° C.

The electrolyte solution 22 operates well in a wide range of current densities.

210 Successful coatings may be applied with a current density ranging from 1 milliamp per square  
centimeter ( $\text{mA}/\text{cm}^2$ ) up to about 1 amp per square centimeter. A more preferred current  
density is from about 3  $\text{mA}/\text{cm}^2$  to about 100  $\text{mA}/\text{cm}^2$ . The actual current density employed is  
dependent on the time the foil strip 14 is exposed to the current. That is, the time the copper  
foil strip 14 is between the anodes 24 and immersed in electrolyte solution 22. Typically, this  
215 dwell time is from about 10 to about 25 seconds. During this dwell, an effective thickness of  
the anti-tarnish coating compound is deposited. The effective thickness is that thickness  
capable of inhibiting copper tarnish at elevated temperatures of up to about 190° C in air for  
about 30 minutes. The anti-tarnish coating should further be sufficiently thin to be easily  
removable with a 4% HCl etch solution or preferably a 5 wt %  $\text{H}_2\text{SO}_4$  etch solution. It is  
220 believed that an effective coating thickness is from less than 100 angstroms to about 0.1  
microns. Successful results have been obtained with coating thicknesses as low as 40  
angstrom and coating thicknesses of from about 10 angstroms to about 100 angstroms are  
preferred. The coating layer is sufficiently thin to appear transparent or impart a slight gray  
tinge to the copper foil 14.

225 The coated strip of copper foil 14 exits the electrolytic cell 10 and is directed by rollers  
28 through the aqueous solution 18 in the silane solution tank 16. The aqueous solution 18  
preferably consists of at least 0.05% silane in DI (deionized) water at a temperature of between  
about 15°C to about 30°C, and more preferably between about 20°C to about 25°C. The  
copper foil 14 is preferably immersed in the aqueous solution 18 for one second or more.

230 The strip of copper foil 14 exits the silane solution tank 16, and any excess electrolyte  
solution 22 and aqueous solution 18 may be rinsed from the surfaces of the copper foil 14. The  
rinse solution may comprise deionized water. More preferably, a small quantity of a caustic is



added to the deionized water rinse solution. The concentration of caustic is quite low, under 1 percent. Preferably the caustic concentration is from about 50 to about 150 parts per million.

235 The caustic is selected to be the hydroxide of an alkali metal or the hydroxide of an alkaline earth metal selected from the group consisting of sodium hydroxide, calcium hydroxide, potassium hydroxide and ammonium hydroxide. Most preferred is calcium hydroxide.

After rinsing, the strip of copper foil 14 may be dried by forced air. The air may be cool (e.g., at room temperature) or heated. Heated forced air is preferred since accelerated  
240 drying minimizes spotting of the copper foil 14.

After drying, the copper foil 14 may then be bonded to a dielectric substrate for forming a printed circuit board or the like using any known lamination process. The dielectric substrate may include, for example, a fiberglass reinforced epoxy such as FR-4 (a fire retardant, glass filled epoxy) or a polyimide such as Kapton manufactured by DuPont. The  
245 lamination process may include bonding the copper foil layer to the dielectric substrate through the use of heat and pressure. For example, a pressure of about 300 psi, at a temperature at about 175° C for a time of up to 30 minutes will provide suitable adhesion between the layers.

#### Surface Treatment 2

250 Referring now to Figure 2, an electrolytic cell 50 for electrodepositing a peel strength enhancement coating on a copper foil, according to a second aspect of the present invention, is shown. The electrolytic cell 50 includes a tank 20 containing an aqueous electrolytic solution 52, and anodes 24 between which the strip of copper foil 14 passes. Guide rolls 26 may be used to control the travel of the strip of copper foil 14 through the electrolytic cell 50. The  
255 guide rolls 26 are manufactured from any material that does not react with electrolyte solution 52. Preferably, at least one of the guide rolls 26 is formed from an electrically conductive material, such as stainless steel, so that a current may be impressed in the strip of copper foil 14 as detailed below. Guide rolls 26 rotate at a controlled speed so that the copper foil 14 is positioned between anodes 24 for a required time as discussed below.

260 In the electrolytic cell 50, a power source (not shown) is provided so that an electric current may pass from the anodes 24 to the strip of copper foil (cathode) 14 by means of the electrolytic solution 52. In this way, a peel strength enhancement coating with the desired composition and thickness is deposited on the foil strip 14.

The electrolytic solution 52 is an aqueous solution containing polyatomic anions that  
265 contain oxygen (oxyanions) formed from a metal selected from groups 5B, 6B, and 7B of the periodic table of the elements. Preferably, the metal is selected from group 6B. Where the

metal is capable of forming more than one oxyanion, the oxyanion containing the larger number of oxygen atoms is preferred (i.e., the “-ate” ion), and the oxyanion containing the largest number of oxygen atoms is most preferred (i.e., the “per\_\_ate” ion). Group 5B  
 270 includes vanadium, niobium, and tantalum. Group 6B includes chromium, molybdenum, and tungsten. Group 7B includes manganese, technetium, and rhenium.

In a preferred composition, the electrolytic solution 52 contains chromate, tungstate, or molybdate ions in DI water, and, for example, consists of about 1 to 200 g/l sodium dichromate. Optionally, about 5 to 100 g/l sodium sulfate or any other conductive salts can be  
 275 added to increase the conductivity of the electrolyte. In a preferred embodiment, the electrolyte solution 52 consists essentially of about 5 to 75 g/l sodium dichromate.

The pH of the electrolyte solution 52 can be maintained in the range of about 0.5 to 14, preferably in the range of about 2 to 10, and most preferably in the range of about 4 to 9. The electrolyte solution 52 readily operates at all temperatures from room temperature up to about  
 280 100° C. For maximum deposition rates, it is preferred to maintain the electrolyte solution 52 temperature in the range of about 20°C to about 80°C, and more preferably between about 40° C to about 60° C.

The electrolyte solution 52 operates well in a wide range of current densities. Successful coatings may be applied with a current density ranging from 5 amps per square foot  
 285 (asf) up to about 200 asf. A more preferred current density is from about 10 asf to about 100 asf, and most preferably from about 30 asf to 70 asf. The actual current density employed is dependent on the time the foil strip 14 is exposed to the current. That is, the time the copper foil strip 14 is between the anodes 24 and immersed in electrolyte solution 52. Preferably, this dwell time is about 2 seconds or more, and more preferably between about 5 to about 25  
 290 seconds. During this dwell time, an effective thickness of a peel strength enhancement coating comprising a metal and metal oxide mixture containing a metal selected from groups 5B, 6B, and 7B of the periodic table of the elements is deposited on the copper foil. When the peel strength enhancement coating is applied to smooth copper foil, the effective thickness is that thickness capable of providing less than or equal to 10% loss of peel strength, when measured  
 295 in accordance with IPC-TM-650 Method 2.4.8.5 using a 1/8 inch wide test specimen, after being immersed in 4N HCl at about 60°C for 6 hours. IPC-TM-650 is available from The Institute for Interconnecting and Packaging Electronic Circuits, 7380 N. Lincoln Avenue, Lincolnwood, Illinois 60646, and is described in further detail below. While the compositions of the treated surface have not been analyzed, it is believed the coating contains a mixture of  
 300 metal and metal oxides with a thickness of about 20 to about 200 angstroms (Å). The

morphology of the coating could also contain some micro-roughness to provide the adhesion enhancement effect.

The coated strip of copper foil 14 exits the electrolytic cell 50 and any excess electrolyte solution 52 may be rinsed from the surfaces of the copper foil 14. The rinse  
 305 solution may comprise deionized water. More preferably, a small quantity of a caustic is added to the deionized water rinse solution. The concentration of caustic is quite low, under 1 percent. Preferably the caustic concentration is from about 50 to about 150 parts per million. The caustic is selected to be the hydroxide of an alkali metal or the hydroxide of an alkaline earth metal selected from the group consisting of sodium hydroxide, calcium hydroxide,  
 310 potassium hydroxide and ammonium hydroxide. Most preferred is calcium hydroxide.

After rinsing, the strip of copper foil 14 may be dried by forced air. The air may be cool (e.g., at room temperature) or heated. Heated forced air is preferred since accelerated drying minimizes spotting of the copper foil 14.

After drying, the copper foil 14 may then be bonded to a dielectric substrate for  
 315 forming a printed circuit board or the like using any known lamination process. The dielectric substrate may include, for example, a fiberglass reinforced epoxy such as FR-4 (a fire retardant, glass filled epoxy) or a polyimide such as Kapton manufactured by DuPont. The lamination process may include bonding the copper foil layer to the dielectric substrate through the use of heat and pressure. For example, a pressure of about 300 psi, at a temperature at  
 320 about 175° C for a time of up to 30 minutes will provide suitable adhesion between the layers.

With reference to FIG. 5, in a typical printed circuit board 90, a dielectric layer 92 has first copper foil layer 94 and second copper foil layer 96 laminated to opposing sides thereof. Each foil layer has a thickness on the order of from 1.0 micron (0.00004 inch) and 5.1 microns (0.0002 inch) and a surface treatment as described above having an average surface roughness,  
 325  $R_z$ , of less than 0.7  $\mu\text{m}$  and preferably, on the order of 0.4  $\mu\text{m}$  to 0.6  $\mu\text{m}$ . The surface treatment is deposited as a nodular structure with an average nodule height of less than 0.75  $\mu\text{m}$ . Preferably, the average nodule height is from 0.3  $\mu\text{m}$  to 0.6  $\mu\text{m}$ . It is believed that the lower surface profile as compared to commercial thin copper foil products enhances stopping of the laser at a back side 100 of the second copper foil layer 96 during laser drilling. A minimum  
 330 average surface roughness of about 0.4  $\mu\text{m}$  is required for a suitable peel strength to prevent delamination of the copper foil.

The copper foil layers 94,96 are formed into desired circuit traces, such as by photolithography. When electrical interconnection between opposing copper foil layers is required, a blind via 98 may be drilled through the first copper foil layer 94 and dielectric layer

335 92 to terminate at the back side 100 of the second copper foil layer 96. Typically, the blind via is drilled using multiple pulses from a CO<sub>2</sub> laser. These pulses, having an energy in the order of 300 microjoules ( $\mu\text{j}$ /pulse) deliver about 3 watts of power at a frequency of 10 kilohertz and complete a blind via in a few seconds.

The laser is intended to drill through the first copper foil layer 94 and dielectric 92, but  
340 not the second copper foil layer 96. If the laser pierces the second copper foil layer, a defect 102 may result. To enhance ablation of the first copper foil layer 94, a laser ablation enhancing layer, such as a dark oxide, may be formed on a surface 104 of the first copper foil layer 94 that is opposite the dielectric 92.

The advantages of the present invention will become apparent from the examples that  
345 follow. The following examples are intended to illustrate, but in no way limit the scope of the present invention.

## EXAMPLES

### Example 1

350 Various comparative and exemplary samples were created using copper foil laminated to an FR4 (glass filled epoxy) dielectric substrate. The copper foil, dielectric substrate, and lamination method used in each of the samples were the same. Different treatment methods were used on the copper foils for each of the samples. Each of the samples was first peel strength tested in accordance with IPC-TM-650 Method 2.4.8.5 using a 1/8 inch wide test  
355 specimen. Next, all but one of the samples were exposed to an 18% HCl solution at 25°C for up to 48 hours and then peel strength tested again in accordance with IPC-TM-650 Method 2.4.8.5 to test the effect of hydrochloric acid (HCl), as may used during the PCB manufacturing process for cleaning of the laminated and photodefined printed circuit board (PCB). The results of these tests are provided in Table 1, which illustrates benefits of the  
360 present invention.

In general, IPC-TM-650 Method 2.4.8.5 describes a test to determine the peel strength of a conductor at ambient temperatures. The test specifies that the test specimen is a laminated copper foil free from such defects as delamination, wrinkles, blisters, cracks, and overetching. The laminated specimen is imaged, then etched, cleaned, and processed using standard  
365 industry practices and equipment. As applied herein, the imaged line is 1/8 inch, and sheared samples with sanded edges are used. Each sample is prepared by peeling back the strip 1 inch so that the line of peel is perpendicular to the edge of the specimen. Each specimen is then secured against a horizontal surface, with the peeled metal strip projecting upward. The end of

the strip is gripped between the jaws of a testing machine clamp, with the jaws covering the  
370 full width of the metal strip and parallel to the line of peel. A suitable testing machine is that  
which is commercially available from Carter Engineering Co., Yorba Linda, CA (Model # TA  
520B10CR). A force is exerted in the vertical plane ( $90 \pm 5^\circ$ ), and the metal foil is pulled at a  
rate of  $2.0 \pm 0.1$  inch-per-minute. The peel strength is determined as the average peel load in  
units of pounds per inch width.

375 Comparative sample 1 was manufactured using a copper foil having a rough,  
CopperBond® treated surface. Comparative sample 1 was also subjected to the P2 treatment  
described hereinabove, where a mixture of chromium and zinc ions or oxides was co-deposited  
on surfaces of the copper foil. Peel strength testing of comparative sample 1 revealed a peel  
strength of about 5.6 pounds per inch (lbs/inch). After 48 hours of exposure to the HCl  
380 solution, comparative sample 1 provided a peel strength of about 4.4 lbs/inch.

Comparative sample 2 was manufactured using a smooth copper foil subjected to the  
P2 treatment only. Peel strength testing of comparative sample 2 revealed a peel strength of  
about 1.6 lbs/inch. Comparative sample 2 delaminated (zero peel strength) after only 1 hour  
of exposure to the HCl solution.

385 Exemplary sample 3 was manufactured in accordance with the first aspect of the  
present invention. The smooth copper foil used in exemplary sample 3 was first given a P2  
treatment and then dipped in a solution of 0.5% silane in DI (deionized) water at approximately  
22°C for one second or more. The sample was then rinsed in DI water and was dried prior to  
lamination. Peel strength testing of comparative sample 3 revealed a peel strength of about 5.5  
390 lbs/inch. After 1 hour of exposure to the HCl solution, comparative sample 3 provided a peel  
strength of about 2.2 to 3.3 lbs/inch.

Comparative sample 4 was manufactured using a smooth copper foil subjected to a dip  
in a solution of 0.5% silane in DI (deionized) water at approximately 22°C for one second or  
more. The sample was then rinsed in DI water and was dried prior to lamination. Peel strength  
395 testing of comparative sample 4 revealed a peel strength of about 1.5 lbs/inch.

Exemplary sample 5 was manufactured in accordance with the second aspect of the  
present invention, where a smooth copper foil was treated in a solution containing dichromate.  
Specifically, the solution contained 15 g/l sodium dichromate and 20 g/l sodium sulfate in DI  
water at cathodic 66 asf and 37°C for 5 seconds or more. Following lamination to FR4 this  
400 treated foil had a peel strength of between 5.3 and 5.5 lbs/inch. After 48 hours of exposure to  
the HCl solution, comparative sample 1 provided a peel strength of about 3.0 to 3.6 lbs/inch.

**Table 1**  
**Effect of Surface Treatment on Peel Strength of Cu Foil**

Sample Number	Treatment Applied to Smooth Cu Surface	As-Laminated Peel Strength	Peel Strength Following HCl Exposure
1 (comparative)	CopperBond® treated + P2	5.6 lb/inch	4.4 lb/inch (48 hr)
2 (comparative)	P2	1.6 lb/inch	0.0 lb/inch (1 hr)
3 (exemplary)	P2 + Dip in 0.5% silane solution (First Aspect)	5.5 lb/inch	2.2-3.3 lb/inch (1 hr)
4 (comparative)	Dip in 0.5% silane solution	1.5 lb/inch	—
5 (exemplary)	Electrodeposition in dichromate solution (Second Aspect)	5.3-5.5 lb/inch	3.0-3.6 lb/inch (48 hr)

As can be seen in Table 1, exemplary samples 3 and 5 each provide a peel strength of about 5.5 lbs/inch, which is much greater than the peel strength provided by the surface treatments used in comparative samples 2 and 4, where only one of the P2 or the silane solution treatment was used. As also shown in Table 1, exemplary samples 3 and 5 provide a peel strength for smooth copper foil that is substantially equal to the 5.6 lbs/inch peel strength observed with a rough, CopperBond® treated foil. Thus, with the surface treatment methods of the present invention, smooth copper foil can have a peel strength substantially equal to that obtained using a conventional, rough-surfaced foil (e.g., a CopperBond® treated foil). This is especially advantageous when extreme fine circuit features or high frequency signal transmittance restricts the degree of surface roughness that may be used. Also, exemplary samples 3 and 5 also show the added benefit of maintaining a peel strength close to that obtained using the CopperBond® treatment, and substantially higher than that of P2 treatment alone, after exposure to HCl.

It was determined that peel strength loss due to HCl exposure is a function of the amount of coating material lost between the copper foil and the dielectric substrate caused by the HCl exposure. Such material loss is referred to herein as “edge undercut”, which can be explained by reference to FIG. 3. FIG. 3a is a cross-sectional view of a copper foil 60 laminated to a dielectric substrate 62 before exposure to HCl. Disposed between the copper foil 60 and the dielectric substrate 62 is a coating material 64, which may be a zinc or chromium-zinc (P2) anti-tarnish coating, or which may be a peel strength enhancement coating in accordance with the second aspect of the present invention. The copper foil 60 and coating material 64 form a portion of a photodefined electrical trace on the PCB. The thickness of the coating material 64 is exaggerated in FIG. 3 for purposes of explanation. Where coating material 64 is a peel strength enhancement coating, for example, the thickness of the coating material may be about 20 to about 200Å.

As can be seen in FIG. 3a, before exposure to HCl, the coating material 64 extends substantially to the side surfaces 66 of the foil 60. Exposure to HCl, which would be used for cleaning the PCB, causes a portion 68 of the coating material 64 proximate the edge surfaces 435 66 to be removed (i.e., undercut), as shown in FIG. 3b. FIG. 3c is a lengthwise view of the strip of foil 60 revealing the undercut coating material 64. As can be seen in FIG. 3c, undercutting of the coating material 64 results in a non-linear edge 70 of the coating material 64.

FIG. 4 is a curve-fit representation of data gathered from the testing of various 440 comparative and exemplary samples created using copper foil laminated to an FR4 (glass filled epoxy) dielectric substrate and depicts peel strength loss (%) as a function of percent undercut. As can be seen from FIG. 4, percent peel strength loss can be represented as a linear function of edge undercut. Thus, the more edge undercut experienced by the sample due to exposure to HCl, the greater the peel strength loss. With regard to the second aspect of the present 445 invention (surface treatment 2), testing has shown that this treatment results in a reduction in both the percent edge undercut and the percent peel strength loss due to HCl exposure, when compared to prior art anti-tarnish coatings. This testing is described below.

Table 2 includes the data used to generate the graph of FIG. 4. The data of Table 2 were generated using a test method in which various comparative and exemplary laminate 450 samples were created using smooth copper foils subjected to different surface treatments. Comparative samples 7-9 represent known surface treatments, while exemplary samples 9-14 represent surface treatments in accordance with the second aspect of the present invention (surface treatment 2). The copper foil, dielectric substrate, and lamination method used in each of the samples of Table 2 were the same, and the samples differed only by the surface 455 treatment used.

For each sample in Table 2, the treated copper foil was laminated to an FR4 dielectric substrate (FR4 PCL 370 having a glass transition temperature ( $T_g$ ) of 175°C). The lamination cycle consisted of 50 minutes heating with a maximum temperature of 182°C and a pressure of 300 psi followed by a 15 minute cooling cycle. The exposed surface of the copper foil was 460 etched in a solution of ammonium persulfate (120 g/l ammonium persulfate plus 3% by volume of concentrated sulfuric acid (about 18 molar) in one liter of DI water) at 44°C for 45 seconds. The sample was then rinsed and dried. Next, the copper foil was plated up to a thickness from about 0.0012 to 0.0016 inches using an acid copper bath without brighteners (60 g/l Cu and 65 g/l sulfuric acid in DI water at 50°C). The desired thickness was obtained in 465 24 minutes using a current density of about 0.065 amps/cm<sup>2</sup>. Using a guillotine paper cutter, ¼

inch wide by 6 inch long test specimens were prepared from each sample, and each specimen was then sheared to 1/8 inch wide using a double edge precision shear. The edges of the specimens were lightly polished using a 600 grit paper to remove any damage that might be introduced by shearing.

470        At least four specimens were prepared for each sample. Half of the specimens (the control specimens) were peel strength tested in accordance with IPC-TM-650 Method 2.4.8.5 without being subjected to HCl. The “As-Laminated” peel strength for the sample is the average peel load for the control specimens in units of pounds per inch width. The remaining specimens were immersed in 4N HCl at 60°C for 6 hours, followed by rinsing and drying. The  
475        exposed specimens were then peel strength tested in accordance with IPC-TM-650 Method 2.4.8.5. In Table 2, the “Peel Strength After 6 Hr HCl Exposure” is the average peel load for the exposed specimens in units of pounds per inch width. Also shown in Table 2 is the percent peel strength loss for each sample, which is equal to the peel strength after 6 hours of HCl exposure expressed as a percentage of the as-laminated peel strength.

480        The percent edge undercut for each sample was determined as follows. First, each exposed specimen was viewed under 100x magnification and the distance between the edge of the coating material to the edge of foil was measured on both sides of the exposed specimen at three different locations. Referring to FIG. 3, for example, these measurements are shown at 72, 74, 76, 78, 80, and 84, with three different measurements being made at each side 66 of the  
485        specimen. After the measurements were made, the average measurement for each side was calculated. The percent undercut for the specimen was then calculated as the sum of the average measurement for both sides expressed as a percentage of the total width of the specimen (1/8 inch). The percent edge undercut for the sample was then calculated by averaging the percent undercut for each specimen associated with the sample. The percent  
490        edge undercut for each sample is provided in Table 2.



**Table 2**  
Effect of Surface Treatment on Peel Strength of Cu Foil

Sample Number	Treatment Applied to Smooth 5µm Cu Foil	As-Laminated Peel Strength (lb/in)	Peel Strength After 6 Hr HCl Exposure (lb/in)	% Peel Strength Loss	% Edge Undercut
6 (comparative)	Commercial Surface Treatment	4.56	4.05	11.2	8.2
7 (comparative)	P2	4.51	3.99	11.5	15.1
8 (comparative)	Zn-Ni	4.14	3.32	19.8	22.0
9 (exemplary)	Chromate w/Si	4.32	4.07	5.8	9.6
10 (exemplary)	Chromate	4.52	4.31	4.7	8.1
11 (exemplary)	Thick Chromate (20s)	4.22	3.92	7.1	6.9
12 (exemplary)	Acidic Chromate	3.88	3.62	6.7	6.0
13 (exemplary)	CDC	4.64	4.55	1.9	8.9
14 (exemplary)	Tungstate	4.29	4.32	-0.7	7.2

495

Each of the samples in Table 2 was prepared using smooth 5µm copper foil.

Comparative samples 6 and 7 were prepared using commercially available copper foils, with sample 7 being a P2 treated foil commercially available as XTF from Olin Corporation of Norwalk, CT. Each of the comparative and exemplary samples 8-14 were prepared using  
500 bare, smooth copper foil having various surface treatments. The Zn-Ni coating of comparative sample 8 was deposited using an aqueous solution containing 10 g/l Ni as sulfate, 3 g/l Zn as sulfate, and 20 g/l citric acid at pH 4, 130°F, while applying 10 asf for 3 seconds and 50 asf for 3 seconds. The chromate with silicate coating of exemplary sample 9 was deposited using an aqueous solution containing 5 g/l Na<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub> · 2H<sub>2</sub>O (1.75 g/l Cr), 10 g/l NaOH, and 10 g/l Na  
505 silicate at 140°F, while applying 20 asf for 10 seconds. The chromate coating of exemplary sample 10 was deposited using an aqueous solution containing 5 g/l Na<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub> · 2H<sub>2</sub>O (1.75 g/l Cr), and 10 g/l NaOH, at 140°F, while applying 20 asf for 10 seconds. The thick chromate of exemplary sample 11 was deposited using the same aqueous solution as that of comparative sample 10, with an increased dwell time of 20 seconds. The acidic chromate of exemplary  
510 sample 12 was deposited using an aqueous solution containing 15 g/l Na<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub> · 2H<sub>2</sub>O, and 20 g/l sodium sulfate at 104°F, while applying 66 asf for 10 seconds. The cathodic dichromate (CDC) of exemplary sample 13 was deposited using an aqueous solution containing 8.75 g/l Cr (25 g/l Na<sub>2</sub>Cr<sub>2</sub>O<sub>7</sub> · 2H<sub>2</sub>O) at pH 4, 140°F, while applying 40 asf for 5 seconds. The tungstate of exemplary sample 14 was deposited using an aqueous solution containing 31 g/l tungsten at  
515 pH4, 140°F, while applying 40 asf for 5 seconds.

As can be seen in Table 2, each comparative and exemplary provided an acceptable peel strength before exposure to HCl of about 4 lb/in. However, after exposure to HCl, the

comparative samples showed a greater percent peel strength loss than did the exemplary samples. The comparative samples provided a percent peel strength loss in the range of 11.2 to 19.8 percent. The exemplary samples, on the other hand, were shown to be effective in providing a percent peel strength loss of less than or equal to 10 percent after being exposed to 4N HCl at 60°C for 6 hours. Indeed, the exemplary samples were effective in providing a percent peel strength loss of less than or equal to about 7 percent. The exemplary samples also showed an improved resistance to edge undercut when compared to smooth foils having a P2 or Zn-Ni coating. It is believed that exposing the copper foil to silane prior to lamination, as in the first aspect of the present invention, would further enhance peel strength of copper foil treated in accordance with the second aspect of the present invention.

The surface treatment methods of the present invention allow the use of smooth copper foil laminates while providing a peel strength substantially equal to that obtained using conventional, rough-surfaced foils. This is especially advantageous when extreme fine circuit features or high frequency signal transmittance restricts the degree of surface roughness that may be used. Also, the surface treatment methods of the present invention provide the added benefit of maintaining a peel strength close to that obtained using rough-surfaced foils, and substantially higher than that of other smooth copper foil treatments, after exposure to HCl. While the invention is particularly useful for use with a smooth copper foil, the invention could be applied to copper foils having any surface finish.

#### Example 2

Copper foils as described in Table 3 were subjected to a single CO<sub>2</sub> pulse of about 300 µj/pulse. Foil A was a commercial product that was purchased from a vendor. Foil B was treated with P2 with an average surface roughness of 1.1 microns as known from the prior art. Foil C was treated with P2 but with the average surface roughness reduced to 0.5 micron. Foil D was treated with the chromate of the invention.

The surface morphology of control foil B is illustrated by a photomicrograph at magnifications of 1000x and 3000x in FIG. 6 and the surface morphology of inventive foil C is illustrated by a photomicrograph at magnifications of 1000x and 3000x in FIG. 7. The foils were also laminated to an FR-4 substrate and peel strength measured as described for Example 1.

550

Table 3 – Laser Ablation

Foil		Surface Roughness ( $\mu\text{m}$ )	Nodule Height ( $\mu\text{m}$ )	Area Ablated ( $\mu\text{m}^2$ )	Peel Strength (lb/inch)	
					FR-4	Polyimide
A	Commercial	1.5	2.0	1300	6.3	
B	P2	1.1	2.5	2100	5.8	16.6
C	P2	0.6	0.5	-0-	4.9	17.2
D	Chromate	0.6	0.5	-0-	4.9	

As can be seen from Table 3, the best combinations of resistance to laser ablation and highest peel strength were achieved by constraining the surface roughness and nodule height to nominals of 0.6 $\mu\text{m}$  and 0.5  $\mu\text{m}$ , respectively.

555

One or more aspects and embodiments of the present invention have been described. Nevertheless, it will be understood that various modifications may be made without departing from the spirit and scope of the invention. Accordingly, other aspects and embodiments are within the scope of the following claims.